



检测报告编号:

F07032200

(2002)量认(国)字(J0746)号

No.L1524



中国石油

中国石油天然气股份公司管道科技研究中心试验测试技术所

PetroChina Pipeline Company Scientific & Technical Center Test Technology Institute

# 检测报告 TEST REPORT

样品名称: SP-2888 防腐涂料 (现场检测)

SAMPLES:

委托单位:

廊坊瑞华石化有限公司

APPLICANT:

检测报告单:

REPORT PAGES:

共1页

报告签发日期:

2007年04月04日

SIGNED DATE:





# 检测报告 TEST REPORT

(2002) 量认(国)字(J0746)号

检测报告编号: F07032200

样品名称: SP-2888 防腐涂料 (现场检测)

样品接收日期: 2007年03月22日

委托单位: 廊坊瑞华石化有限公司

检测开始日期: 2007年03月22日

委托日期: 2007年03月22日

检测结束日期: 2007年03月22日

样品型号: SP-2888

样品批号: ---

样品描述: ---

检测报告正文:

序号	测试项目	单位	测试结果	执行标准	
1	附着力 (拉开法)	对钢管	MPa	15.49	ASTM D 4541
		对 PE 层	MPa	11.32	ASTM D 4541
2	固化时间(固化温度 55 °C)	min	5	实测	

测试人员: 冯利河

### 有效性声明:

1. 本报告所出具的检测结果仅对所检测样品负责。
2. 本报告由审核人、技术负责人签字, 并加盖相应印鉴后有效。
3. 本报告涂改、手工填写(签名除外)、报告编号和合同编号前后不一致均视为无效。
4. 未经本机构书面允许, 部分使用本报告原件及复印件均视为无效。
5. 本报告抱怨/申诉期为 30 天, 自报告签发日期起计算。

第 1 页 共 1 页 (报告结束, 以下无正文)

审核人:   
**AUDIT PERSONNEL:**

批准人 (检测专用章):   
**TECHNICAL MANAGER:**



中国石油天然气股份有限公司管道科技研究中心试验测试技术所

PetroChina Pipeline Company Scientific & Technical Center Test Technology Institute

通信地址: 河北省廊坊市金光道 51 号 Address: Jinguang Road No.51 Langfang, Hebei, China  
邮政编码: 065000 电话/传真: 0316-2073691 Post code: 065000 Tel/Fax: (86)316-2073691

未经书面许可, 部分使用本报告的原件及复印件均视为无效。本报告无签字和相应印鉴无效。  
The report is effective after sealed and subscribed. The report shall not be reproduced except in full, without the written approval of our laboratory.

中国实验室国家认可 (CNAL No. L1524)  
CHINA NATIONAL ACCREDITATION OF LABORATORIES

国家计量认证单位  
(2002) 量认(国)字(J0746)号